



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-41-589-0010

FAX 82-41-589-0012

Report No : TAK-2019-032700

Receipt Date : 2019.02.22.

Representative : KIM DONG HOO

Test Completion Date : 2019.03.18.

Company name : DAEYANG PLATEC

Address : 24, Nonggongdanji-gil, Hapdeok-eup, Dangjin-si, Chungcheongnam-do, Rep. of KOREA

Sample name : Pliable plastics conduits KS C 8454 (CD 36)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Outer diameter	mm	-	41.67	KS C 8454 : 2006
Pliability(Room temperature)	-	-	No Defects	KS C 8454 : 2006
Pliability(-25 °C)	-	-	No Defects	KS C 8454 : 2006
Compression resilience(reduction of the outer diameter)	%	-	2	KS C 8454 : 2006
Compression resilience(appearance)	-	-	No Defects	KS C 8454 : 2006
Impact Test	-	-	No Defects	KS C 8454 : 2006
Deformation By Flexure Resistance	-	-	No Defects	KS C 8454 : 2006
Deformation By Heat Resistance	-	-	No Defects	KS C 8454 : 2006
Dielectric strength	-	-	No Defects	KS C 8454 : 2006
Insulation Resistance	MΩ	-	Test More than 100	KS C 8454 : 2006
Tensile test	-	-	No Defects	KS C 8454 : 2006
Flame Resistance(Self-extinguishing property)	-	-	No Defects	KS C 8454 : 2006

- Usage of Report : For approval of supply source

- Next Page -

Na Hong Seok

Prepared by Na Hong Seok

Tel : 02-2092-3706

You Seok

Reviewed by You Seok

Tel : 1577-0091(ARS ①→④)

2019.03.18

Korea Testing & Research Institute

President *Byun, Jong-Rip*



QR Code for forgery



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-41-589-0010

FAX 82-41-589-0012

Report No : TAK-2019-032700

Receipt Date : 2019.02.22.

Representative : KIM DONG HOO

Test Completion Date : 2019.03.18.

Company name : DAEYANG PLATEC

Address : 24, Nonggongdanji-gil, Hapdeok-eup, Dangjin-si, Chungcheongnam-do, Rep. of KOREA

Sample name : Pliable plastics conduits KS C 8454 (CD 36)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
-----------	------	--------	--------	-------------

- Note :
1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
 2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
 3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Na Hong Seok

Prepared by Na Hong Seok

Tel : 02-2092-3706

You Seok

Reviewed by You Seok

Tel : 1577-0091(ARS ①→④)

2019.03.18

Korea Testing & Research Institute

President *Byun, Jong-Rip*



QR Code for forgery